



TIMBER PRODUCTS
 We Deliver Confidence. ®

TP Audit Sample Report - Pellet Program

E09-9001
 LIGNETICS
 141 Old Sharon Road
 Jaffrey, NH 03452

TP ID Number:	PF1240324-1	Sample Weight (lbs):	39.44
Product / Commodity:	Wood Pellets / 40 lb bag	Sample Received:	8/12/2024
Date Stamp:	11104213	Report Date:	10/7/2024
Inspector:	Matt Emerle	Production Date:	7/31/2024
Date of Inspection:	8/2/2024	Facility Registration #:	TP003
Sample Grade:	Premium	PFI Quality Mark:	Yes
Material Type:	Blended	Purchase Order #:	

Parameter	As-Received	Dry Basis	Pass/Fail	Analytical Method	ISO 17025
Total Moisture (%)	4.75		P	ASTM E871	Q
Ash (%)	0.49	0.52	P	ASTM D1102	Q
GCV (BTU/lb)	8184	8592	P	ISO 18125	Q
Chlorine (ppm)	< 50	< 50	P	ISO 16994	Q

Parameter	Result	Pass/Fail	Analytical Method	ISO 17025
Bulk Density (lb/ft³)	41.3	P	PFI Specifications	Q
Length (%) > 1.5 Inches	0.00	P	PFI Specifications	Q
Diameter (mean)	0.259	P	PFI Specifications	Q
Fines (%)	0.35		PFI Specifications	Q
Durability Index	98.5	P	PFI Specifications	Q



Prepared By:

David Robles - Laboratory Manager

Findings are based on the sample submitted. TP Inspection is accredited by the International Accreditation Service (IAS) to ISO 17025. All test parameters above are included in TP Inspection's scope of accreditation. Pass/Fail limits are based on the as-received values reported above. All conformity statements use the "Simple Acceptance" decision rule per ILAC-G8-*Guidelines on Decision Rules and Statements of Conformity*. This report shall not be reproduced except in full without laboratory approval. All BEL services are subject to our laboratory terms and conditions, a copy of which can be accessed through the following link: [TP Terms & Conditions](#)