



TIMBER PRODUCTS
We Deliver Confidence. ®

TP Audit Sample Report - Pellet Program

E09-9134
LIGNETICS
95 Energex Drive, State Road 75
Mifflintown, PA 17059

TP ID Number: PFI260270-1
Product / Commodity: Wood Pellets / 40 lb bag
Date Stamp: 060826D1
Inspector: Jeromy Tapper
Date of Inspection: 6/16/2026
Sample Grade: Premium
Material Type: Blended

Sample Weight (lbs): 40.30
Sample Received: 6/24/2026
Report Date: 7/2/2026
Production Date: 6/8/2026
Facility Registration #: TP012
PFI Quality Mark: Yes
Purchase Order #:

Parameter	As-Received	Dry Basis	Pass/Fail	Analytical Method	ISO 17025
Total Moisture (%)	5.32		P	ASTM E871	Q
Ash (%)	0.60	0.63	P	ASTM D1102	Q
GCV (BTU/lb)	8025	8476	P	ISO 18125	Q
Chlorine (ppm)	< 50	< 50	P	ISO 16994	Q

Parameter	Result	Pass/Fail	Analytical Method	ISO 17025
Bulk Density (lb/ft³)	44.7	P	PFI Specifications	Q
Length (%) > 1.5 Inches	0.00	P	PFI Specifications	Q
Diameter (mean)	0.258	P	PFI Specifications	Q
Fines (%)	0.15		PFI Specifications	Q
Durability Index	99.0	P	PFI Specifications	Q



Prepared By:

Chris Wiberg

Chris Wiberg - Vice President of Laboratories

Findings are based on the sample submitted. TP Inspection is accredited by the International Accreditation Service (IAS) to ISO 17025. All test parameters above are included in TP Inspection's scope of accreditation. Pass/Fail limits are based on the as-received values reported above. All conformity statements use the "Simple Acceptance" decision rule per ILAC-G8-*Guidelines on Decision Rules and Statements of Conformity*. This report shall not be reproduced except in full without laboratory approval. All BEL services are subject to our laboratory terms and conditions, a copy of which can be accessed through the following link:
[TP Terms & Conditions](#)